

Roof therm D bitumfiber

Beton  **Wood**

Ecological systems for thermo-acoustic insulation of wood fiber Therm and wood fiber Bitumfiber roofs

Complete isolation systems for high performance wooden roofs



| DESCRIPTION

The complete natural insulating system for wood roof with high performances Roof **SolutionD bitumfiber** is ideal for home wellness and comfort in all climatic zones.

The Roof **SolutionD bitumfiber** system is characterized by excellent thermal, acoustic and breathability insulation values which reduces mold and moisture formation better than the traditional systems.

The materials used are completely natural and made with sustainable raw materials and life cycles.

The stratigraphy consists of FSC® certified **FiberTherm** wood fiber panels with a density of 160Kg/m³ and a single layer of **Bitumfiber** bituminous wood fiber panels with a density of 280Kg/m³, between the matchboard and the wood fiber insulation the **FiberTherm multi membra5** perfectly airtight steam brake is applied, while, on the external side below the roof tiles **FiberTherm multi UDB** must be installed, a high performance sheath, breathable and UV resistant.

The system is applicable for roofs with a minimum slope of 15° and up to 900 m s.l.m.


Advantages

- Construction permeable to steam and resistant to driving rain
- For highly inclined roofs with slopes starting at 15°, resistant to UV rays
- Complete system: insulation, under cloth and waterproofing without condensation
- Excellent protection against cold and summer heat, improved acoustic insulation thanks to the porosity of the panels
- High performance thanks to rational installation and without waste

For more informations about the uses and the installation, our offices are ready to answer your questions on www.betonwood.com






STRATIGRAPHY



- 1 **Roof tiles**
- 2 **Block-tiles battes** Wooden battens to support tiles, parallel to the eaves line and with a pitch related to the roof tile.
- 3 **Battens for ventilation** Battens perpendicular to the gutter line directly on the insulating panel, the strips will have suitable fastening all'assito adhesion with the underlying wood, the distance of the strips is to be assessed according to the load of its own structure and the external loading actions. Thanks to the air gap, the air enters the eaves and rises to the surface, absorbing most of the heat produced by the sun's rays.
- 4 **FiberTherm multi UDB** High airtight sealant vapor barrier for renovation solutions. Extreme ease of installation for safe and simple use. It has an integrated adhesive strip to secure joints and can be used as a temporary cover.
Size: 1,50 m x 50 m Roll surface: 75m² Weight approx.160 g/m²
- 5 **Bituminous wood fiber Bitumfiber 280** | thickness 23 mm Panel in bituminous wood fiber density 280 Kg/m³ with high compressive strenght and excellent insulating properties. Panel dimensions 2400 x 1200 mm. Edge with sharp edge
- 6 **Wood fiber FiberTherm 160** | thickness 100+100 mm Panel in wood fiber density 160 Kg/m³ is offered as an excellent insulation for both the summer heat and the winter frost. Depending on requirements, the thickness can be varied with panels with thickness 80 + 80 mm or 60 + 60 mm. Panel dimensions 1350 x 600 mm. Edge with sharp edge
- 7 **FiberTherm multi membra5** Steam brake for better airtightness on the outer side of the roof, resistant to UVrays, excellent adhesion properties and tear resistance. Size: 1,50 mx50 m Roll surface: 75m² Weight approx.110 g/m²
- 8 **Concrete structure roof** | thickness 200+40 mm
- 9 **Plaster** | thickness 10 mm

THERMAL DISPLACEMENT



ZONE C

Solution DB - type C1

FiberTherm 100 + 100 mm
Bitumfiber 23 mm

Transmittance $U = 0,156 \text{ W} / (\text{m}^2\text{K})$
Resistance $R = 6,425 (\text{m}^2\text{K}) / \text{W}$
Displacement 31,46 hours
Climatic zone C

Solution DB - type C2

FiberTherm 80 + 80 mm
Bitumfiber 23 mm

Transmittance $U = 0,186 \text{ W} / (\text{m}^2\text{K})$
Resistance $R = 5,373 (\text{m}^2\text{K}) / \text{W}$
Displacement 29,02 hours
Climatic zone C

Solution DB - type C3

FiberTherm 60 + 60 mm
Bitumfiber 23 mm

Transmittance $U = 0,231 \text{ W} / (\text{m}^2\text{K})$
Resistance $R = 4,320 (\text{m}^2\text{K}) / \text{W}$
Displacement 26,16 hours
Climatic zone C

ZONE D

Solution DB - type D1

FiberTherm 100 + 100 mm
Bitumfiber 23 mm

Transmittance $U = 0,156 \text{ W} / (\text{m}^2\text{K})$
Resistance $R = 6,425 (\text{m}^2\text{K}) / \text{W}$
Displacement 31,47 hours
Climatic zone D

Solution DB - type D2

FiberTherm 80 + 80 mm
Bitumfiber 23 mm

Transmittance $U = 0,186 \text{ W} / (\text{m}^2\text{K})$
Resistance $R = 5,373 (\text{m}^2\text{K}) / \text{W}$
Displacement 29,02 hours
Climatic zone D

Solution DB - type D3

FiberTherm 60 + 60 mm
Bitumfiber 23 mm

Transmittance $U = 0,231 \text{ W} / (\text{m}^2\text{K})$
Resistance $R = 4,320 (\text{m}^2\text{K}) / \text{W}$
Displacement 26,16 hours
Climatic zone D

ZONE E

Solution DB - type E1

FiberTherm 100 + 100 mm
Bitumfiber 23 mm

Transmittance $U = 0,156 \text{ W} / (\text{m}^2\text{K})$
Resistance $R = 6,425 (\text{m}^2\text{K}) / \text{W}$
Displacement 31,46 hours
Climatic zone E

Solution DB - type E2

FiberTherm 80 + 80 mm
Bitumfiber 23 mm

Transmittance $U = 0,186 \text{ W} / (\text{m}^2\text{K})$
Resistance $R = 5,373 (\text{m}^2\text{K}) / \text{W}$
Displacement 29,02 hours
Climatic zone E

Solution DB - type E3

FiberTherm 60 + 60 mm
Bitumfiber 23 mm

Transmittance $U = 0,231 \text{ W} / (\text{m}^2\text{K})$
Resistance $R = 4,320 (\text{m}^2\text{K}) / \text{W}$
Displacement 26,15 hours
Climatic zone E



| SYSTEM'S PRODUCTS



FiberTherm **multiUDB** Membrana sigillante in polipropilene (PP) multi-strato non-tessuto ad alta traspirabilità ed ottima resistenza allo strappo. Densità 160 g / m²



Bitumfiber The bituminous wood fiber panel is the optimal combination for high strength in dry and wet screed construction. The material is characterized by the following thermodynamic characteristics: density approx. 280 (+20-10) kg/m³, coefficient of thermal conductivity $\lambda=0,050$ W/mK, coefficient of resistance to vapor penetration $\mu=5$, specific heat $c=2100$ J/Kg K and reaction to fire class E, according to EN 13501-1 standard, CE certified. The wood used in the processing of the panels comes from forests controlled by FSC reforestation cycles.



FiberTherm The panels are made of wood fiber with density $\delta=160$ Kg/m³, are produced with a wet system, in compliance with EN 13171 and EN 13986 standards under constant quality control. The material is characterized by the following thermodynamic characteristics: coefficient of thermal conductivity $\lambda=0.039$ W/mK, specific heat $c=2100$ J/Kg K, coefficient of resistance to vapor penetration $\mu=5$ and reaction to fire class E, according to EN 13501-1 standard. The dimensions of the panels correspond to ... mm for a thickness of ... mm. The wood used in the processing of the panels comes from forests controlled by FSC reforestation cycles.



FiberTherm **multi membrà 5** Steam brake for better airtightness on the outer side of the roof, resistant to UV rays, excellent adhesion properties and tear resistance.

BETONWOOD Srl

Head offices :
Via Falcone e Borsellino, 58
I-50013 Campi Bisenzio (FI)

T: +39 055 8953144
F: +39 055 4640609

info@betonwood.com
www.betonwood.com

TDB - STR.18.9

| CERTIFICATIONS

The Solution D bitumfiber roof insulation system is produced with CE certified materials in accordance with the regulations in force.

The certificates of the individual products are available on request.

Beton Wood

